



prime tac

700 Series

750 | 7 Mil General Purpose Multi-Purpose Duct Tape

Our Primetac™ 750 premium duct tape is built with a natural rubber adhesive that resists curling for a convenient and reliable application. The 750 also bonds well to most surfaces and has good all-weather performance.

GENERAL PURPOSE



Clean Removal



Outdoor Durable



Built for Bundling



Hand-Tearable



Built for Irregular Surfaces

BUILT FOR



Specifications

Adhesive

Natural Rubber

Total Thickness

7 mil | 178 microns
ASTM D-1000

Adhesion to Steel

65 oz / in (7.11 N / cm)
PSTC-101

Tensile Strength

21 lb / in (36.8 N / cm)
ASTM D-1000

Operating Temperature

40°F - 200°F (4°C-93°C)

Features

- Environmentally friendly & safe to use (Low VOC)
- Hand tearable and conformable
- Resists twisting and curling
- Bonds well to most surfaces
- Good all-weather performance

Other Physical Properties

Property	Backing	Adhesion to Backing PSTC-101	Elongation ASTM D-1000	VOC Content
Standard	PE Coated Cloth	38 oz / in	19%	<1 g/L
Metric	PE Coated Cloth	4.16 N / cm	19%	<0.12 oz/gal

Tested in accordance with UL 723

Applications

- Maintenance and general repair
- Joint sealing and pipe wrapping
- Bundling, patching and mending
- Heavy-duty carton sealing

Storage and Usage

Suggested Storage Conditions:

- 16°C - 27°C (60°F-80°F), or as close as possible to room temperature.
- 40-60% max relative humidity
- Original packaging in a cool, dry area away from direct sunlight exposure and from freezing.

Suggested Application Conditions

- Surfaces to which tape is applied should be clean, dry and free of dust, grease, oil or other contaminants.

Available Product Options

Stock Lengths



55m

Stock Widths



48mm

Types



Hand



Machine

Colors

Silver

We customize! Contact a representative for special sizes and colors.

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The physical and performance characteristics shown are averages obtained from tests recommended by PSTC procedures in our laboratory and the user must by test or otherwise determine suitability for his purpose. There is no warranty of fitness for a particular purpose. Primetac does not take responsibility for the defective material if not stored and used in accordance with the conditions listed above. This specification sheet might change due to the continuous improvement for better quality product.