



## prime tac

800 Series (Flatback)

# 848 | 4.9 Mil General Purpose Flat-Back Paper Tape

Our Primetac<sup>™</sup> premium 848 is a good, economical choice for carton sealing with its quick stick and excellent adhesion. Specially developed for the movers industry. Matches most corrugated cardboard.

 GENERAL PURPOSE




Built for Boxes



Easy & Even Unwind



Quick Tack



Pilfer-Proof



Hand-Tearable

## BUILT FOR



### Specifications

#### Adhesive

Hot Melt Adhesive

#### Backing

70 g/ Kraft Paper

#### Total Thickness

4.9 mil | 125 microns  
ASTM D-3652

#### Tensile Strength

20 lb / inch (3.6 kg / cm)  
ASTM D-3759

#### Operating Temperature

23°F - 140°F (-5°C - 60°C)

### Features

- ✓ Built for recycled corrugated and non-unitized loads
- ✓ Versatile and positive attractive seal
- ✓ Get peace of mind with pilfer-proof, tamper evident tape
- ✓ Matches most corrugated cardboard
- ✓ Quick stick and excellent adhesion
- ✓ RoHS compliant

### Other Physical Properties

Property	Holding Power ASTM D-3654	Elongation ASTM D-3759
Standard	>24 h	1.5 - 3%
Metric	>24 h	1.5 - 3%

### Applications

- Carton sealing
- Moving and storage
- Roll-to-roll splices
- Picture framing

### Storage and Usage

#### Suggested Storage Conditions:

- 4°C - 26°C (39°F-79°F), or as close as possible to room temperature.
- 40-50% Max Relative Humidity
- Original packaging in a cool, clean, dry area away from direct sunlight exposure.

#### Suggested Application Conditions

- Surfaces to which tape is applied should be clean, dry and free of dust, grease, oil or other contaminants.

Available Product Options

### Stock Lengths



50m

### Stock Widths



48 mm

**We customize! Contact a representative for special sizes.**

### Types



Hand



Machine



### Colors

Natural

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The physical and performance characteristics shown are averages obtained from tests recommended by PSTC procedures in our laboratory and the user must by test or otherwise determine suitability for his purpose. There is no warranty of fitness for a particular purpose. Primetac does not take responsibility for the defective material if not stored and used in accordance with the conditions listed above. This specification sheet might change due to the continuous improvement for better quality product.