



## prime tac

800 Series (Flatback)

# 850 | 7.7 Mil Performance Grade Flat-Back Paper Tape

Our Primetac<sup>TM</sup> premium 850 is an excellent choice for carton sealing where high holding and easy tearing is required. Specially developed for the movers industry.



PERFORMANCE GRADE



Built for Boxes



Easy & Even Unwind



Quick Tack



Pilfer-Proof



Hand-Tearable

## BUILT FOR



Retail



Construction



Appliance



Transportation



Fulfillment



Arts & Crafts



Moving & Storage

### Specifications

#### Adhesive

Rubber - Resin

#### Backing

Flat Back Paper

#### Total Thickness

7.7 mil | 200 microns

ASTM D-3652

#### Adhesion to Steel

68.1 oz / inch (0.76 kg / cm)

ASTM D-3330/M

#### Tensile Strength

52.6 lbs / inch (9.4 kg / cm)

ASTM D-3759

### Features

- ✓ Built for recycled corrugated and non-unitized loads
- ✓ Performs in high tension and temperature demanding processes.
- ✓ Get peace of mind with pilfer-proof, tamper evident tape
- ✓ Superior durability to keep tape intact
- ✓ Good tensile strength
- ✓ RoHS compliant

### Other Physical Properties

Property	Adhesion to Backing ASTM D-3330/M	Elongation ASTM D-3759
Standard	25.6 oz / in	3%
Metric	.285 kg / cm	3%

Test Condition: Temperature: 23°C ± 2°C (73.4°F ± 3.6°F) | Relative Humidity: 50% ± 5%

### Applications

- Carton sealing
- Moving and storage
- Roll-to-roll splices
- Picture framing

### Storage and Usage

#### Suggested Storage Conditions:

- 15°C - 30°C (59°F-86°F), or as close as possible to room temperature.
- 60% Max Relative Humidity
- Original packaging in a cool, dry area away from direct sunlight exposure and from freezing.

#### Suggested Application Conditions

- Surfaces to which tape is applied should be clean, dry and free of dust, grease, oil or other contaminants.

Available Product Options

### Stock Lengths



50m

### Stock Widths



48 mm



72 mm

### Types



Hand



Machine



### Colors

Dark Brown

We customize! Contact a representative for special sizes.

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The physical and performance characteristics shown are averages obtained from tests recommended by PSTC procedures in our laboratory and the user must by test or otherwise determine suitability for his purpose. There is no warranty of fitness for a particular purpose. Primetac does not take responsibility for the defective material if not stored and used in accordance with the conditions listed above. This specification sheet might change due to the continuous improvement for better quality product.